

PureMatte®

Nanotechnology

Anti-Bacterial Surface

ISO22196 tested to diminish 99.99% bacteria in 24 hours




Anti-Bacterial
Surface



Scratch Resistant
Self-healing



Chemical
Resistant



Mold Resistant



Stain Resistant



Anti-fingerprint
Technology



Greenguard
Certified

Through vigorous research and application of nanotechnology we bring you peace of mind with PureMatte's spectacular surface properties, a breakthrough ultra-durable surface technology that is as beautiful as it is functional

ISO22196 tested. Diminishing 99.99% bacteria in 24 hours


Sizes

2440 x 1220 or 3660 x 1220


Colours




Dove




Raven



Mist




Syrah



Atlantic




Riverstone




Milford




Raven



Mist



Shadow



Atlantic



Cocoa

1 Testing

IFAM tested two coating systems according to JIS Z 2801-2012 (ISO 22196-2011).

In consultation with the customer, the following test organisms were used for all the experiments. Table 1 lists the test organisms and their international reference numbers.

Organisms:	Sample Number:
Escherichia coli	ATCC 8739, DSMZ 1576
Staphylococcus aureus	ATCC 6538P, DSMZ 346
Salmonella choleraesuis (Salmonella enterica)	subsp. enterica Serovar Typhimurium (Syn. Salmonella choleraesuis) DSMZ 5569
Pseudomonas aeruginosa	DSMZ 1253

2 Coating Systems

The test parameters prescribed by the standard are shown in table 2

Reference	50 x 50 x 2 mm, Glass
Samples	50 x 50 x 0.15 mm, Coating
Film	40 x 50 x 0.05 mm, PE-Foil (16 cm ²)
Suspension medium	400 µL 1/500 nutrient broth (NB)
Temperature & contact time	36°C, 24 h
Flush medium / neutralisation	9.6 mL SCDLP broth
Cultivation medium	Hefeextrakt-Pepton-Agar (HEA)
Evaluation process	Dilution series, Plate casting process (ISO 6222)

Except for slightly elevated viable cell counts per cm² (U₀) for *Escherichia coli* (2.75 x 10⁴) and *Salmonella enterica* (3.25 x 10⁴), the test and validation parameters corresponded to the values set down in the standard.

The slightly elevated values had no influence on the test result because even for these test organisms there was complete reduction of the viable cell counts down to the detection limit.

Organism	Reference		Sample 1		Sample 2	
	U _n	U _t	A _t	R>*	A _t	R>*
Escherichia coli	4.44	5.99	-0.20	6.15	-0.19	6.18
Salmonella enterica	4.51	5.52	-0.19	5.72	-0.24	4.43
Staphylococcus aureus	4.38	4.19	-0.17	4.36	-0.24	4.43
Pseudomonas aeruginosa	4.29	6.46	-0.25	6.71	-0.23	6.79

$$*R = (U_t - U_0) - (A_t - A_0)$$

3 Conclusions

Tests according to ISO 22196 show that sample 1 and sample 2 coatings had **very high antimicrobial activity** (R > 3) for all the bacteria that were tested.

After 24 h contact time on the two coatings, **more than 99.99% of the original bacteria were no longer detectable** (namely the concentration was below the statistical detection limit of 10 cells per 400µL suspension medium).